

# Sika® Primer-206 G+P

## Technical Product Data

Chemical base	Pigmented, solvent-based adhesion promoter	
Colour	Black	
Density (CQP <sup>1</sup> 006-3 / ISO 2811-1)	1.0 kg/l approx.	
Viscosity <sup>2</sup> (CQP 029-3 / ISO 3219)	10 mPa·s approx.	
Flash point (CQP 007-1 / ISO 13736)	-4°C (25°F)	
Solid content	40%	
Application temperature	5 - 40°C (40 - 105°F)	
Application	Brush, felt or foam applicator	
Coverage	50 - 150 ml per m <sup>2</sup> approx. depending on substrate porosity	
Flash-off time <sup>3</sup>	above 15°C (60°F) below 15°C (60°F) maximum	10 min 30 min 24 hours
Storage	Store in sealed container in a cool dry place below 25°C (75°F)	
Shelf life	9 months	

<sup>1)</sup> CQP = Corporate Quality Procedure

<sup>2)</sup> 23°C (73°F) / 50% r.h.

<sup>3)</sup> In specific applications temperature and flash-off time may be different

Industry

### Description

Sika® Primer-206 G+P is a black, moisture-curing liquid primer specifically formulated for the treatment of bond faces prior to application of Sika® polyurethane adhesives. Sika® Primer-206 G+P is manufactured in accordance with ISO 9001 / 14001 quality assurance system and the responsible care program.

### Areas of Application

Sika® Primer-206 G+P is used to give improved adhesion in adhesive bonding applications on substrates such as glass, ceramic-coated glass and painted surfaces. Sika® Primer-206 G+P can also be used on other substrates such as plastics and some metals. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

### Method of Application

Surfaces must be clean, dry and free from grease, oil and dust. Apply Sika® Aktivator using the wipe-on, wipe-off method and allow flashing off. Shake the can of Sika® Primer-206 G+P very thoroughly until mixing ball rattles freely. Continue shaking for another minute and apply a thin but covering coat with a brush, felt pad or foam applicator. Ideal application and surface temperature is between 15°C and 25°C (60°F to 75°F). Consumption and method of application depend on the specific nature of the substrates and manufacturing process. Sika® Primer-206 G+P should be applied once only. Care must be taken to ensure that this single application gives adequately dense coverage. Tightly re-seal container immediately after each use.



### Important Note

Sika® Primer-206 G+P should be used within one month after opening the can.

### Further Information

Working instructions issued for a defined application may further specify technical data contained in this Product Data Sheet. Copies of the following publications are available on request:

- Material Safety Data Sheets
- Sika Pre-treatment Chart

### Packaging Information

Can	30 ml
	250 ml
	1 l

### Value Bases

All technical data stated in this Product Data Sheet are laboratory test based. Current measured values may vary do to factors beyond our influences.

### Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.



Further information available at:

[www.sika.co.id](http://www.sika.co.id)

PT. Sika Indonesia, Jl. Raya Cibinong-Bekasi Km.20,  
Limusnunggal, Cileungsi, Bogor - Indonesia  
Tel: +62 21 8230025, Fax: +62 21 8230026

