

Product Data Sheet

ABC 880 FILL&FIX POLYURETHANE GUN FOAM

Product Description

It is a fast curing one-component foam. There are two types with and without gun. Fill & Fix inflates up to 50 times the packaging volume. Within 1-2 hours of curing (at 25 C and 50% humidity). Can be cut, sanded and painted.

Areas for Use

- Door and window assembly.
- For filling irregular voids in stone, brick or concrete.
- To take precaution before turning off the power cables.
- For gaps in the gaps passing through the wall.

Properties/Benefits

- Ideal for sound and heat insulation.
- It does not contain any propellant which may damage the ozone layer.
- After drying, it can be painted, cut and sanded.
- Economic use

Product Information

Chemical Structure Polyurethane

Packaging In 750 ml (850g) packages

Colours Light Yellow

Storage and Shelf life In its original unopened and undamaged package, it is suitable for 15 months from date of manufacture if stored in dry conditions between + 5 ° C and + 25 ° C protected from direct sunlight.

Product Data Sheet

ABC 880 FILL&FIX POLYURETANNE GUN FOAM

Technical Properties

Chemical Structure	Polyurethane
Curing System	Moisture
Density	23±3 kg/m ³
Tack Free Time	10 dak
Fire Class of the cured foam	B3
Tensile Strenght	9 N/cm ²
Compression Strenght	4 N/cm ²

Product Data Sheet

ABC 880 FILL&FIX POLYURETHANE GUN FOAM

Application

- The surface used must be clean, free of dust and small particles that are broken. Moisturized surfaces increase the speed of curing and allow less foam to be used..
- Always wear protective glasses and gloves.
- Shake at least 20 times before use
- When using foam with gun, make sure the gun snaps into the foam and do not apply pressure to it.
- Always apply upside down.
- Any excess foam can be cleaned with ABCFoam Cleaener when wet.
- The fixing element should be used in windows and joinery until complete curing takes place.

Legal Requirements

The information contained herein and in particular on the application and end use of ABC products are provided in good faith based on the current knowledge and experience of the ABC, in normal circumstances and in the case of ABC recommendations, where these products are properly stored, treated and applied. For this reason, when using ABC products, make sure that you apply the right product in the right conditions and in the right place. Otherwise, ABC is not responsible for any damages

ABC Kimya Sanayi ve Dış Ticaret A.Ş.

Ortaköy Mah. İltar Bulvarı No: 16
Selimpasa 34582 Silivri / İstanbul / Türkiye

İletişim

Tel: +90 212 422 13 56 (Pbx)
Fax: +90 212 422 13 58
www.abcsealants.com